SANSEI PAINT Co.,Ltd.

1261-5 Nukatabe-kitamachi Yamato-kohriyama Nara, JAPAN
TEL 0743-56-8611 FAX 0743-56-8621 Zip code : 639-1037
URL:http://www1.kcn.ne.jp/~kikyou/ *E.mail:kikyou@kcn.ne.jp*

SANSEI PAINT SANSEI PAINT

【¥S30E50】

Nitorocellulose Lacquer Top Coat

Safety-Lacquer Clear

"**Safety-Lacquer Clear**" is an ample, and quick-drying nitoro-cellulose top coat which renders very clear gloss surface shortly after application.
It does not contain formaldehyde, Toluene, Xylene, DOP, nor DBP.

Field of application

"**Safety-Lacquer Clear**" is used for finsh the surface of wood.

Surface Preparation

Surface must be sound, clean, dry and free of wax, grease, oil and sanding dust.

Thinner

Lacqer Thinner (Safety-Lacquer Thinner is recomennded)

Method of Application

Apply with brush, painting pad or spray. Use of roller may cause air bubbles.
Let dry 2−3 hours.

Covering Capacity

8-15 Sq.m/Litre (dependent on method of application and coat thickness)

Drying Time

To the touch in 10-20 minutes.
Piling dry in 1−3 hours depending upon weather conditions and air circulation.

Derections for use

"Safety-Lacquer Clear" is applied in 1 or 2 coats(wet on wet or wet on dry) on many kinds of wood.

Application

"Safety-Lacquer Clear" is mixed with thinner in the mentioned mixing ratio and applied in one coat.

Packing

3.5kg and 15kg

SANSEI PAINT Co.,Ltd.

1261-5 Nukatabe-kitamachi Yamato-kohriyama Nara, JAPAN
TEL 0743-56-8611 FAX 0743-56-8621 Zip code : 639-1037
URL:http://www1.kcn.ne.jp/~kikyou/ *E.mail:kikyou@kcn.ne.jp*

SANSEI PAINT SANSEI PAINT

【¥S30E50】

Nitorocellulose Lacquer Top Coat

Safety-Lacquer Flat

"**Safety-Lacquer Flat**" is an ample, and quick-drying nitoro-cellulose top coat which renders very clear mat surface shortly after application.
It does not contain formaldehyde, Toluene, Xylene, DOP, nor DBP.

Field of application

"**Safety-Lacquer Flat**" is used for finsh the surface of wood.

Surface Preparation

Surface must be sound, clean, dry and free of wax, grease, oil and sanding dust.

Thinner

Lacqer Thinner (Safety-Lacquer Thinner is recomennded)

Method of Application

Apply with brush, painting pad or spray. Use of roller may cause air bubbles.
Let dry 2−3 hours.

Covering Capacity

8-15 Sq.m/Litre (dependent on method of application and coat thickness)

Drying Time

To the touch in 10-20 minutes.
Piling dry in 1−3 hours depending upon weather conditions and air circulation.

Derections for use

"Safety-Lacquer Flat" is applied in 1 or 2 coats(wet on wet or wet on dry) on many kinds of wood.

Application

"Safety-Lacquer Flat" is mixed with thinner in the mentioned mixing ratio and applied in one coat.

Grade

Gloss: 30%, 50%, 70%, 100%

Packing

3.5kg and 15kg