SANSEI PAINT Co.,Ltd.

1261-5 Nukatabe-kitamachi Yamato-kohriyama Nara, JAPAN
TEL 0743-56-8611 FAX 0743-56-8621 Zip code : 639-1037
URL:http://www1.kcn.ne.jp/~kikyou/ *E.mail:kikyou@kcn.ne.jp*

SANSEI PAINT SANSEI PAINT

【¥S30E50】

Nitorocellulose Lacquer Sanding Sealer

Safety-Lacquer Sanding Sealer

"**Safety-Lacquer Sanding Sealer**" is an ample, and quick-drying nitoro-cellulose sanding sealer which renders very fine sanding properties shortly after application.
It does not contain formaldehyde, Toluene, Xylene, DOP, nor DBP.

Field of application

"**Safety-Lacquer Sanding Sealer**" is used for smoothing the surface of wood.

Surface Preparation

Surface must be sound, clean, dry and free of wax, grease, oil and sanding dust.
Sand bare wood surface smooth and remove all sanding dust.

Thinner

Lacqer Thinner (Safety-Lacquer Thinner is recomennded)

Method of Application

Apply with brush, painting pad or spray. Use of roller may cause air bubbles.
Let dry 2−3 hours then sand lightly with a fine,(#240 then #320),sandopaper to make surface smooth. Then remove dust completely. The surface is now ready for an application of varnish such as Clear Lacquer or Lacquer Flat.

Covering Capacity

8-15 Sq.m/Litre (dependent on method of application and coat thickness)

Drying Time

To the touch in 10-20 minutes.
Topcoat in 1−3 hours depending upon weather conditions and air circulation.

Derections for use

"Safety-Lacquer Sanding Sealer" is applied in 1 or 2 coats(wet on wet or wet on dry) on many kinds of wood.

Application

"Safety-Lacquer Sanding Sealer" is mixed with thinner in the mentioned mixing ratio and applied in one coat.

Packing

3.5kg and 15kg